

Plasti-Paste™ II

Trowelable Plastic Paste



www.smooth-on.com

PRODUCT OVERVIEW

New Plasti-Paste™ II is a two component fiber-filled resin that is designed for vertical surface application. This no-odor formulation is an improved version of our original Plasti-Paste™ formula, and the cured product is different in the following ways: **1. Plasti-Paste II is now phthalate free.** **2. Cured plastic can be painted** (original Plasti Paste™ can not) and **3. It is harder, more rigid with better heat resistance.** Part A is a liquid and Part B is a paste. **New Mix Ratio is 1A: 2B by volume (62A:100B by weight).** Pot life is 10 minutes at room temperature depending on mass. Demold time (can be handled) is about 90 minutes at room temperature depending on mass. Full cure; 24 hours at room temperature. Cure time can be accelerated by applying heat.

Mixed material holds a vertical surface without sagging and cures to a strong, durable and lightweight plastic. Liquid material can be pigmented with So-Strong™ color tints from Smooth-On. This plastic can be used for creating themed environments or special effects, used as a “mother mold” material to reinforce rubber molds and a variety of other applications. **This plastic is also a powerful adhesive** and can be used as a repair material for a variety of industrial applications. Cured plastic can be sanded, machined and painted with acrylic enamel paints.

TECHNICAL OVERVIEW

Mix Ratio: 1A:2B by volume 62A:100B by weight

Mixed Viscosity: Paste (ASTM D-2393)

Specific Gravity, g/cc: 1.0 (ASTM D-1475)

Specific Volume, cu. in. /lb.: 27.73 (ASTM D-1475)

Pot Life: 10 minutes @ 73° F/23°C (ASTM D-2471)

Demold Time: 90 minutes @ 73° F/23°C **

Color: Off White

Shore D Hardness: 70D (ASTM D-2240)

Ultimate Tensile, psi: 2150 (ASTM D-638)

Tensile Modulus, psi: 235,000 (ASTM D-638)

Elongation @ Break: 1.14% (ASTM D-638)

Flexural Strength, psi: 3840 (ASTM D-790)

Flexural Modulus, psi: 203,000 (ASTM D-790)

Compressive Strength, psi: 4,980 (ASTM D-695)

Heat Deflection Temp: 130°F/55°C (ASTM D-648)

Compressive Modulus, psi: 62,700 (ASTM D-695)

Shrinkage, in./in.: 0.005 in./in. (ASTM D-2566)

* All values measured after 7 days at 73°F/23°C

** Depending on mass

PROCESSING RECOMMENDATIONS

Preparation – Materials should be stored and used in at room temperature (73° F / 23° C). This product has a limited shelf life and should be used as soon as possible. Mixing should be done in a well-ventilated area. Wear safety glasses, long sleeves and rubber gloves to minimize contamination risk. If making a 2 or more piece mother mold, apply appropriate shim apparatus to rubber mold exterior. Use in a low humidity environment (below 50% RH). Mixing containers should have straight sides and a flat bottom. Mixing sticks should be flat and stiff with defined edges for scraping the sides and bottom of your mixing container. **Because no two applications are quite the same, a small test application to determine suitability for your project is recommended if performance of this material is in question.**

Plasti-Paste™ II Coverage Rates - Gallon Unit

Applied at 3/8"/0.95 cm	Applied at 1/2"/1.27 cm
961 in ² /6199 cm ² (6.7 ft ² /0.6 m ²)	720 in ² /4645 cm ² (5.0 ft ² /0.5 m ²)

Applying A Release Agent – This product is adhesive and will bond to many surfaces. A sealer followed by a release agent is necessary to facilitate demolding when applying as a mother mold over a cured mold rubber. Use Sonite™ Wax followed by a coating of Universal™ Mold Release or Ease Release 200 release agent. A liberal coat of release agent should be applied onto all surfaces that will contact the plastic. You can also apply aluminum foil as a barrier over the surface followed by an application of Mold Release agent.

Stir Part A and shake Part B thoroughly before dispensing. – Part B is a thick paste containing oil that needs to be pre-mixed before being dispensed into measuring container. Dig deep to re-disperse oil & paste components that may have separated.

Measuring – The components of Plasti-Paste™ II requires two different sized containers. The first will be used for measuring out amounts of Part A and Part B. The second should be large enough to contain both components and allow thorough mixing. **IMPORTANT:** Shelf life of Part A (Yellow Container) is reduced after opening. Remaining product should be used as soon as possible. XTEND-IT™ Dry Gas Blanket will prolong shelf life of unused liquid urethanes.

Mixing – Mix Ratio is 1A:2B by volume (62A:100B by weight). **(Step 1)** Fill measuring container to the top with Part B paste, making sure to eliminate any air voids. Level off the top of the container and remove any excess material. The paste should then be thoroughly emptied into a larger container that will act as your mixing container. **Repeat As Necessary. (Step 2)** Fill the measuring container to the top with Part A liquid and empty into mixing container. Mix thoroughly for 2-3 minutes making sure that you scrape the sides and bottom of the mixing container several times. Eliminate color streaks.

Safety First!

The material safety data sheet (MSDS) for this or any Smooth-On product should be read before using and is available on request. All Smooth-On products are safe to use if directions are read and followed carefully. **Keep Out of Reach Of Children.**

Plasti-Paste™ II PART A:

WARNING: IRRITANT TO EYES, SKIN & MUCOUS MEMBRANES.

Contains Methylene Diphenyl Isocyanate and Polymethylene Polyphenylisocyanate. Do not get in eyes, mucous membranes or on skin. Do not take internally. Do not breathe fumes. Use only with adequate ventilation. Wear chemical-resistant gloves and eye protection when using this product.

First Aid: In case of eye contact, flush thoroughly with water for 15 minutes and get immediate medical attention. In case of skin contact, wash thoroughly with soap and water. If irritation persists, get medical attention. If swallowed, do not induce vomiting. Drink 1 - 2 glasses of water and get immediate medical attention.

If vapors are inhaled or if breathing becomes difficult, remove person to fresh air. If symptoms persist, get medical attention. **Keep Out Of Reach Of Children.**

Plasti-Paste™ II PART B:

CAUTION: In case of eye contact, flush with water for 15 minutes. If irritation persists, get medical attention. For skin contact, wash with soap and water.

Keep Out Of Reach Of Children.

IMPORTANT: The information contained in this bulletin is considered accurate. However, no warranty is expressed or implied regarding the accuracy of the data, the results to be obtained from the use thereof, or that any such use will not infringe upon a patent. User shall determine the suitability of the product for the intended application and assume all risk and liability whatsoever in connection therewith.

IMPORTANT: Shelf life of product is reduced after opening. Remaining product should be used as soon as possible. Immediately replacing the lids on both containers after dispensing product will help prolong the shelf life of the unused product. **XTEND-IT™ Dry Gas Blanket** (available from Smooth-On) will significantly prolong the shelf life of unused liquid urethane products.

If adding So-Strong™ color tints, pre-mix color with the Part B before adding Part A.

Mixing Large Batches - A 'Turbine' mechanical mixer attached to a power drill will make mixing large batches of material much easier. Visit www.smooth-on.com to learn more about these inexpensive mixers.

APPLYING, CURING & HEAT RESISTANCE

Applying – Mixed material thickens quickly and pot life is limited. Do not delay between mixing and applying. To increase working time, spread entire container contents over rubber mold surface and cover and spread mixture to uncovered areas. Apply uniformly with spatula over mold surface. Material will adhere to itself if additional layers are needed. Apply at least 3/8" (1 cm) thickness, making sure rubber mold is thoroughly covered. **For maximum strength** and heat resistance, 1/2" (1.27 cm) thickness is recommended. Large molds may require added thickness for support shell stability. Supports (wood or metal) may be embedded for added stability and handling. **Prevent a jagged surface;** Final layer of Plasti-Paste™ II can be smoothed by wiping solvent (denatured alcohol or acetone) onto surface with gloved hand.

Making A Two Piece Shell – Plasti-Paste™ II will bond to most surfaces and itself tenaciously. A barrier coat of paste wax followed by Universal™ Mold Release applied to all surfaces is necessary to prevent adhesion. Applying aluminum foil to the contours of all surfaces followed by Universal™ Mold Release will also prevent adhesion.

If You Want To Paint Cured Plastic – For best results, measure 62 Parts A + 100 Parts B by weight using a gram scale.

Curing – Plastic will be hot immediately following cure. Let cool to room temperature before handling. Material will develop handling strength and can be handled in about 90 minutes depending on mass. At this point, it is stable enough to demold, re-assemble over rubber mold and make a casting (hold 2 or more piece assemblies together with elastic bands, mold straps or bolts). Large sections should be bolted together to minimize distortion. Full strength develops in 24 hours.

Heat Resistance – Fully cured plastic with a minimum thickness of 1/2" (1.27 cm) will resist temperatures up to 130°F/55°C. To improve heat resistance to 158°F / 70°C, post cure material at 150°F/65°C for 16 hours.

If machining or sanding cured plastic, wear NIOSH approved mask to prevent inhalation of residual particles.

PAINTING & STORAGE

Painting – Make sure surface is clean and free of release agents or other contaminants. Cured plastic can be painted and/or primed and then painted with acrylic enamel paints. Let paint fully dry before putting part into service.

Storage – For best storage results, cast into rubber mold with a gypsum plaster or other dimensionally stable material, assemble mold inside the Plasti-Paste™ II support shell and store assembled molds on a level surface indoors at room temperature in a dry place.



Call Us Anytime With Questions About Your Application.

Toll-free: (800) 381-1733

Fax: (610) 252-6200

The new www.smooth-on.com is loaded with information about moldmaking, casting and more.